

# Product datasheet UNIQ+ pd

### 1 Description of the product / intended use / company

Trade name: UNIQ+ pd

Intended use: Thermoplastic foils for the manufacture of

appliances and splints for dental and

orthodontic treatments.

Manufacturer / Supplier: Scheu Dental GmbH

Am Burgberg 20 58642 Iserlohn

Germany

Tel. 0049 2374 9288-0

# 2 Composition / information on ingredients

**Chemical characterization** 

CAS-Number:

Designation: Copolyester/ Polyethylene (PE)

With a removable protective film!

#### 3 Handling and storage

Handling

Information for safe handling: When using do not eat, drink or smoke.

Provide suction extractors if dust is formed.

Storage

Storage conditions: Store dry and dark at 5 - 35 °C

# 4 Physical, chemical, mechanical and biological properties

# 4.1 General properties

Properties	Guideline	Value	
Form	1	Solid	
Colour	-	Transparent	
Odour	-	Odourless	
Density	ASTM D 1505	1,19 g/cm <sup>3</sup>	
Water absorption after 24 h at 23°C	ASTM D 570	0,5 %	

Revision: 0 07/24 Replaced:	Page 1 von 2
--------------------------------	--------------



# Product datasheet UNIQ+ pd

# 4.2 Mechanical properties

Properties	Guideline	Value
Tensile strength	ASTM D 882	41 MPa
E-modulus	ASTM D 882	1462 MPa
Elongation at yield	ASTM D 882	7 %
Elongation at break	ASTM D 882	179 %

#### 4.3 Thermal properties

Properties	Guideline	Value
Glass transition temperature	DSC	110 °C

#### 4.4 Biological properties / Biocompatibility

A biological evaluation was carried out for the material in accordance with DIN EN ISO 10993-1. It meets the requirements regarding biocompatibility for medical devices.

# 5 Stability and reactivity

#### Thermal decomposition / Conditions to avoid:

No decomposition by intended use.

#### 6 Disposal

The material can be recycled after separation or deposed of like commercial or household waste.

The aforementioned data are given most conscientiously but without any obligation. Any processing details are provided merely for guidance: it is the user's responsibility to check the suitability of the product for the intended application.

Revision: 0 07/24 Replaced:		Page 2 von 2
--------------------------------	--	--------------